

Test Report

Testing institute : Product Technology Service (Ningbo) Co., Ltd.
5-7F, 59#, Huayu Road,
Yinzhou District, Ningbo 315192 P.R.China

Applicant : NINGBOYUNHAI CLEANING PRODUCTS CO.,LTD.
1001, Yujia Village, Gulin Town, Yinzhou District
Ningbo, Zhejiang, China/315177

Product name : Disposable waterproof plastic apron

Model No. : FH01

Sample description : blue

Material : CPE

Sample receive date : May 07,2020
Completes date : May 08,2020

Testing location : Product Technology Service (Ningbo) Co., Ltd.

Test specification(s) : Conclusion
1.Visual inspection Pass
2.Hydrostatic pressure test Pass
3.Tensile strength See result

Jinli Zhang

Originator:
Jinli Zhang

Shengmin Gu

Report Verifier:
Shengmin Gu

Meng Wei

Authorizer :
Meng Wei

Product Technology Service (Ningbo) Co., Ltd.

Ningbo, May 08, 2020

The test results exclusively refer to the samples examined. The test report is only used for scientific research, teaching or internal quality control. This report shall not be reproduced except in full without written approval and does not authorize the use of Product Technology Service (Ningbo) Co., Ltd. label. The report is invalid without signature and seal of Product Technology Service (Ningbo) Co., Ltd.

1.Test specification : Visual inspection
 Test method : According to GB 19082-2009

Product name	Requirement	Result	Conclusion
Disposable waterproof plastic apron	1、 The protective clothing should be dry, clean, free of mildew, and no defects such as adhesion, cracks, holes, etc on the surface. 2、 The parts of protective clothing such as bonding or heat sealing should be flat 、 sealed and without bubbles.	1、 The sample is dry, clean, free of mildew, and no defects such as adhesion, cracks, holes, etc on the surface. 2、 The parts of The sample such as bonding or heat sealing is flat 、 sealed and without bubbles.	Pass

2.Test specification : Hydrostatic pressure test
 Test method : GB/T 4744-2013,Evaluation by GB 19082-2009

Product name	Requirement (cmH ₂ O)	Result (cmH ₂ O)	Conclusion
Disposable waterproof plastic apron	≥17	59	Pass

3.Test specification : Tensile strength
 Test method : According to GB/T 3923.1-2013
 gauge length 100mm, constant rate of extension 100mm/min

Product name	Result		
	--	Break load [N]	Elongation [%]
Disposable waterproof plastic apron	Length	12	375
	Width	14	343

Main test instruments used for this method:

Instrument	Manufactory	Model / Type
CRE testing machine	INSTRON	3366

Sample photo(s), see annex 1

---End---

Product Technology Service

Report No.:NB2020050721

Page 3 of 3

ANNEX 1

Sample photo, consists of 1 page



Disposable waterproof plastic apron